


tempio

Rustikotta skin

Technical data sheet



Rustikotta Prime

RKP280600 225x500x28mm

For use in coating vertical façades

Colours

EK1005 Red flamed · EK1009 Light Grey Flamed · EK1014 White September
EK1024 Antique Moss · EK1027 Black Oxid · EK1038 Tampico · EK1051 New Black

Water absorption	EN ISO 10545-3	Group All _{a-2} (3%<E<6%)
Breaking load (225x500mm)	EN ISO 10545-4	> 1200 N
Frost resistance	EN ISO 10545-12	Fulfilled
Resistance to thermal shock	EN ISO 10545-9	Fulfilled
Impact resistance (by measurement of coefficient of restitution)	EN ISO 10545-5	0.7-0.9
Fire resistance	-	Clase A1
Stain resistance	EN ISO 10545-14	Group 5 (Glazed)
Chemical resistance	EN ISO 10545-13	Group GA (Glazed)
Linear thermal expansion	EN ISO 10545-8	$5.75 \cdot 10^{-6} \text{ K}^{-1} (\pm 1)$

Tolerances and dimensions

Weight	-	3.9 kg/piece ± 0.5 kg
Width	In extruding direction	± 4.0 mm
Height	Opposite to extruding direction	± 2.0 mm
Thickness	EN ISO 10545-2	28.0 mm ± 1.0 mm
Straightness (in extruding direction)	EN ISO 10545-2	± 1.5 mm
Ortogonalit	EN ISO 10545-2	± 2.0 mm
Flatness		± 2.0 mm